

Pompoms & Tassels

PERFORMANCE	TEST METHOD	REQUIREMENT
INITIAL PACKAGE / FULL PACKAGE		
Physical Properties		
Individual Strand Length	Kohl's TM-8	Report Actual Measurement in mm
Construction Quality	Kohl's TM-10	All strands in place and of equal length, no glued, fused or bonded parts as approved by Kohl's Tech Team
Appearance Retention		
Appearance Retention after Laundering AND Dry Cleaning	AATCC/ASTM TS-008 Modified Ultra Tide® Powder Detergent	Color Change: Grade 4 min. Staining: Grade 4 min.
Strength & Durability		
Attachment Pull Strength (Individual Strand)	16 CFR 1500.51-53 Pt F modified	For Sizes 0-4T: No detachment at 17 lbs. for 10 seconds For sizes over 4T & Adults: 5 lbs. for 10 seconds
Attachment Pull Strength (Whole Pompom/Tassel)	16 CFR 1500.51-53 Pt F modified	For Sizes 0-4T: No detachment at 17 lbs. for 10 seconds For sizes over 4T & Adults: Report Actual Value
Pompom Safety/Size attachment standard (test only if pompom detaches)	ASTM F 963-08 Sec. 4.35	Pass - Pompom must not pass through the test fixture Refer to Kohl's Safety Policy
Colorfastness		
Colorfastness to Chlorine Bleach AND Non-Chlorine Bleach	AATCC/ASTM TS-001	Shade Change: Grade 4 min
Colorfastness to Crocking	AATCC 8/116	Dry - Grade 4 min Wet - Grade 3 min
ADDITIONAL COLORWAY TESTING		
Appearance Retention after Laundering AND Dry Cleaning	AATCC/ASTM TS-008 Modified Ultra Tide® Powder Detergent	Color Change: Grade 4 min. Staining: Grade 4 min.
Colorfastness to Chlorine Bleach AND Non-Chlorine Bleach	AATCC/ASTM TS-001	Shade Change: Grade 4 min
Colorfastness to Crocking	AATCC 8/116	Dry - Grade 4 min Wet - Grade 3 min
REQUIRED WHERE APPLICABLE AT ADDITIONAL COST		
	Kohl's TM-5 (only for 4 years and up)	Negative. If Spot Test is Positive, proceed with step 2
	JIS L 1041:2000 –	Children <u>over 4</u> & Adults = 75 ppm max.
Formaldehyde	Sec. 5.3.1 (2) Method B, JIS Water Extraction Method	Children's 0-4T = 20 ppm max.
Resistance to Saliva* (Children Only - under 36 months)	64 LFGB B82.10-1	Staining: Grade 4.5 min Shade Change 4.0 min
TOXICOLOGY TESTING – REQUIRED WHERE APPLICABLE AT ADDITIONAL COST		
Lead Content in Surface Coating - Scrapeable in each color*	CPSC-CH-E1003-09.1	Children & Adult Products ≤ 90ppm (0.009% by weight) Refer to Kohl's Product Safety Policy for additional requirement on Composite Testing
Total Lead in Substrate Material*	CPSC-CH-E1002-08.1/ CPSC-CH-E1001-08.1	Children's of ALL ages & Adult products ≤100 ppm (0.010% total weight) Refer to Kohl's Product Safety Policy for additional requirement on Composite Testing
Phthalates in each plasticized part/material such as PVC, Vinyl*	CPSC-CH-C1001.09.3	Children's & Adult Products (Coatings Shall be tested) ≤1000 ppm (0.1%) in each part of DEHP, DBP, BBP, DINP, DIDP, DNOP, & DNHP Refer to Kohl's Product Safety Policy for additional requirement on Composite Testing
Soluble Heavy Metals* Applies to Children's Toys	ASTM F 963-11	Children's Toys = Defined as a consumer product designed or intended by the manufacturer for a child, for use by the child when the child plays. Required for children's toys of ALL ages Mercury – 60 ppm Antimony – 60 ppm Arsenic – 25 ppm Selenium – 500 ppm Barium – 1000 ppm Cadmium – 75 ppm Chromium – 60 ppm Lead – 90 ppm
(*) asterisk= ALL COLORWAYS MUST BE TESTED		

Pompoms & Tassels

PERFORMANCE	TEST METHOD	REQUIREMENT
Minimum Sample Size Necessary for Testing		
Initial Package: 4 mock ups of darkest colorway		
Additional Colorway: 2 mock ups per colorway		
Toxicology Testing		
Consult with approved lab for the number of samples		
**Please refer to Kohl's preferred third party labs for individual and optional testing pricing		
If Formaldehyde Spot Test is found positive, additional charges will incur for additional testing.		
For sizes 0-4T, Formaldehyde will be added as a separate charge as it is a mandatory test for this category.		
Turn Around Time = 6 working days		
PROTOCOL VERSION	DESCRIPTION OF CHANGE	DATE REVISION / APPROVED BY
305-1	<ol style="list-style-type: none"> Appearance Retention – Changed test method to AATCC/ASTM TS-008 Modified. Lead Content for Scrapable Surfaces – Changed requirement from 600 ppm to 90 ppm. Added – Lead Content Total Substrate, Heavy Metal Content, Phthalate and Formaldehyde test for children's products 	Nov. 2008/Ro Jain
305-2	<ol style="list-style-type: none"> Lead Content in Surface coating – Updated test method to CPSC-CH-E1003-09 Lead in Substrate – Updated test method to CPSC-CH-E1002/CPSC-CH-E1001-08 and requirement <100 ppm from spring 2011 Phthalates – Updated test method to CPSC-CH-C1001.09.2, added DNHP and applies to all children's products 	Nov. 2009/Ro Jain
305-3	<ol style="list-style-type: none"> KAR Test – Added "Ultra" to Tide Detergent. Individual Strand Length - Assigned test method # to Kohl's TM-8. Construction Quality – Assigned test method # to Kohl's TM-10. Lead in Surface Coating – Updated method to CPSC-CH-E1003-09.1. Added Adult requirement, <90 ppm. Total Lead Substrate – Updated method to CPSC-CH-E1002-08.1/CPSC-CH-E1001-008.1. Phthalates – Updated method to CPSC-CH-C1001-09.3. Added Adult requirement, <1000 ppm. Heavy Metals – Updated method to ASTM F963-08. Attachment Pull Strength (individual strand) – Provided requirement for sizes over 4T & Adults at 5 lbs. for 10 seconds. Pompom Safety /Size attachment standard – Updated method to ASTM F 963-08, Sec. 4.35. Refer to Safety Policy. Resistance to Saliva – Changed method from Section 35 LMBG 82.10 to 64 LFGB B82.10-1. Added Shade Change requirement. 	Nov. 2011/Amy Her
305-4	<ol style="list-style-type: none"> Lead in Substrate test – Starting Spring 2013, test is required on Adult products. Toxicology tests required on both Children & Adult products. 	Sept. 2012 / Vinoth Deenadayalan
305-5	<ol style="list-style-type: none"> Toxicology tests REQUIRED WHERE APPLICABLE. Updated Heavy Metals Test method to ASTM F963-11. 	Jan. 2013/ Vinoth Deenadayalan
305-6	<ol style="list-style-type: none"> Removed "starting spring 2013" statement Added "coatings shall be tested" statement to the Phthalates test Formaldehyde – Modified JIS method to Water Extraction. Updated Children 0-4T req. from 0.05 Absorbency to 20 ppm. 	May 2013/ Vinoth Deenadayalan
305-7	Removed pricing for testing/took out Intertek/added approved lab statement	October 6th 2014/Nov. 31 2014/Leah Gross-Hutchison